

GPO PRICE \$ _____

CFSTI PRICE(S) \$ _____

NASA CR-72065


R-6754-3

3

Hard copy (HC) 3.00

Microfiche (MF) 1.65

ff 653 July 65



PROPERTIES OF NONAQUEOUS ELECTROLYTES

THIRD QUARTERLY REPORT

(20 December 1966 to 19 March 1967)

By
Rudolf Keller
James N. Foster
John F. Hon
Jack M. Sullivan

Prepared For

National Aeronautics and Space Administration

Contract NAS3-8521

N67-26628	(THRU)	(CODE)	CR-72065	(CATEGORY)
	(PAGES)	(NASA CR OR TMX OR AD NUMBER)		

FACILITY FORM 602

Rocketdyne
A Division of North American Aviation, Inc.
Canoga Park, California

NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the National Aeronautics and Space Administration (NASA), nor any person acting on behalf of NASA:

- A.) Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use **of** any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or
- B.) Assumes any liabilities with respect to the use of, or for damages resulting from the use **of** any information, apparatus, method or process disclosed in this report.

As used above, "person acting on behalf of NASA" includes any employee or contractor of NASA, or employee of such contractor, to the extent that such employee **or** contractor of NASA, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with NASA, or his employment with such contractor.

Requests for copies of this report should be referred to

National Aeronautics and Space Administration
Office of Scientific and Technical Information
Attention: AFSS-A
Washington, D.C. 20546

NASA CR-72065
R-6754-3

PROPERTIES OF NONAQUEOUS ELECTROLYTES
THIRD QUARTERLY REPORT

(20 December 1966 to 19 March 1967)

By

Rudolf Keller
James N. Foster
John F. Hon
Jack M. Sullivan

Prepared For

National Aeronautics and Space Administration

19 April 1967

Contract NAS3-8521

Technical Management
NASA Lewis Research Center
Cleveland, Ohio
Space Power Systems Division
Mr. Robert B. King

Rocketdyne
A Division of North American Aviation, Inc.
Canoga Park, California

FOREWORD

This report was prepared under G.O. 8852 in compliance with Article VI and Paragraph B of Contract NAS3-8521 for the National Aeronautics and Space Administration, Lewis Research Center, Cleveland, Ohio. The work was conducted in the Chemical and Material Sciences Department of Rocketdyne's Research Division, during the period 20 December 1966 through 19 March 1967.

ABSTRACT

A complete vapor phase chromatographic analysis of acetonitrile was conducted. A method was established for the routine characterization of purified solvent batches of propylene carbonate, dimethyl formamide and acetonitrile; the water content of each solvent is determined quantitatively to ± 5 to 10 ppm.

Structural studies of electrolytes containing tetramethylammonium hexafluorophosphate, tetramethylammonium fluoride, and AlCl_3 were performed by nuclear magnetic resonance.

The physical property studies included measurements of viscosities, conductances, transference numbers, and solubilities of a number of electrolytes.



CONTENTS

Foreword	iii
Abstract	iii
Summary	1
Description of Progress	3
Preparation of Electrolytes	3
Purification of Solvents	3
Analysis of Acetonitrile by Vapor Phase Chromatography	4
Routine Characterization of Distilled Solvents	12
Nuclear Magnetic Resonance Structural Studies	13
TMA•PF ₆ and TMA•F in Propylene Carbonate and Dimethyl Formamide	13
AlCl ₃ in Dimethyl Formamide	14
Physical Property Determinations	21
Viscosity Measurements	21
Solubility Measurements	23
Conductance Measurements	26
Measurement of Transference Numbers by the Hittorf Method	42
Work Planned for Next Quarter	59
Preparation of Electrolytes	59
Nuclear Magnetic Resonance Structural Studies	59
Physical Property Determinations	59
References	61



ILLUSTRATIONS

1. Initial Portion of Chromatogram of Acetonitrile Containing 120 ppm Water	6
2. Chromatogram of Acetonitrile, AN #1-2, on Apiezon L . . .	9
3. Chromatogram of Acetonitrile, AN #1-2, on Carbowax 20M . .	10
4. Chromatogram of Acetonitrile, AN #1-2, on Porapak Q . . .	11
5. H^1 Spectrum for $(TMA)^+$	15
6. H^1 Spectrum for Pure DMF	16
7. H^1 Spectrum for 0.0528 M $AlCl_3/DMF$	17
8. H^1 Spectra, Methyl Doublet at High Resolution, in Pure DMF .	19
9. H^1 Spectrum of Methyl Protons in 0.0528 M $AlCl_3/DMF$. . ,	20
10. Equivalent Conductance of LiCl in Propylene Carbonate at 25 and 60 C	34
11. Equivalent Conductance of LiCl in Propylene Carbonate at 25 and 60 C	35
12. Equivalent (Molar) Conductance of $AlCl_3$ in Propylene Carbonate at 25 and 60 C	36
13. Equivalent (Molar) Conductance of $LiCl + AlCl_3$ in Propylene Carbonate at 25 to 60 C	37
14. Comparison of Equivalent (Molar) Conductances of Electrolytes Containing LiCl and/or $AlCl_3$ in PC at 25 and 60 C	38
15. Equivalent Conductance of $TMA \cdot PF_6$ in PC at 25 and 60 C . .	46
16. Equivalent Conductance of $TMA \cdot PF_6$ in PC at 25 and 60 C . .	47
17. Equivalent Conductance of $TMA \cdot PF_6$ in DMF at 25 and 60 C . .	48
18. Equivalent Conductance of $TMA \cdot PF_6$ in DMF at 25 and 60 C . .	49
19. Equivalent Conductance of $TMA \cdot PF_6$ in AN at 25 and 60 C . .	50
20. Equivalent Conductance of $TMA \cdot PF_6$ in AN at 25 and 60 C . .	51
21. Hittorf Cell Schematic	52
22. Hittorf Cell	53



TABLES

1. Distillation Procedures for Purification of Solvents	3
2. Characterization of Distilled Solvent Batches	4
3. Columns Employed in the Characterization of Acetonitrile	5
4. Area of Water Peak for Solutions of Acetonitrile Containing Various Amounts of Water	7
5. Experimental Parameters and Response for the Routine Determin- ation of Water in Propylene Carbonate, Dimethyl Formamide, and Acetonitrile	12
6. Viscosity Determinations at 25 C	22
7. Solubility Determinations	24
8. Solute Concentrations Determined by Nuclear Magnetic Resonance	27
9. Summary of Conductance Measurements	29
10. Specific Conductance (Λ) and Equivalent Conductance (Λ) of LiCl/ PC at 25 and 60 C	30
11. Specific Conductance (λ) and Equivalent Conductance (Λ) of AlCl ₃ / PC at 25 and 60 C	31
12. Specific Conductance (Λ) and Equivalent Conductance (Λ) of AlCl ₃ / PC at 25 and 60 C	32
13. Specific Conductance (Λ) and Equivalent Conductance (Λ) of LiCl+ AlCl ₃ /PC at 25 and 60 C	33
14. Comparison of Conductance Values of 0.05 M LiCl, 0.05 M AlCl ₃ , and 0.05 M LiCl + 0.05 M AlCl ₃ Solutions in PC and DMF	41
15. Specific Conductance (Λ) and Equivalent Conductance (Λ) of TMA·PF ₆ /PC at 25 and 60 C	43
16. Specific Conductance (λ) and Equivalent Conductance (Λ) of TMA·PF ₆ /DMF at 25 and 60 C	44

17. Specific Conductance (λ) and Equivalent Conductance (Λ) of TMA•PF ₆ /AN at 25 and 60 C	45
18. Determinations of Transference Numbers (t) of LiCl in DMF by the Hittorf Method	55
19. Hittorf Experiment With an Electrolyte Containing 1 M LiCl and 0.1 M CuCl ₂ in DMF	57



SUMMARY

Acetonitrile (AN) was completely analyzed by vapor phase chromatography; no organic impurity at a level greater than 10 ppm was found in the distilled product. A convenient vapor phase chromatographic analysis method is now available to determine the water content in each batch of distilled solvent.

Nuclear magnetic resonance structural studies revealed that tetramethylammonium hexafluorophosphate ($\text{TMA} \cdot \text{PF}_6$) was present in propylene carbonate (PC) and dimethylformamide (DMF) as TMA^+ and PF_6^- ions. AlCl_3 coordinates with DMF molecules at the oxygen site rather than the nitrogen site; between 4 and 8 (probably 6) moles of coordinated solvent are produced per dissolved mole of AlCl_3 .

Viscosities and conductances were measured for a number of electrolytes containing $\text{TMA} \cdot \text{PF}_6$, LiCl , and/or AlCl_3 . Solubilities are listed for such electrolytes, and also for some others containing LiF , $\text{TMA} \cdot \text{F}$ (tetramethylammonium fluoride), and CuCl_2 . Transference number determination by the Hittorf method indicated a low transference number for the cation in LiCl/DMF and the presence of a negatively charged copper species in such an electrolyte which also contained CuCl_2 .



DESCRIPTION OF PROGRESS

PREPARATION OF ELECTROLYTES

Purification of Solvents

Solvents were purified by distillation as described previously (Ref. 1 and 2). A summary of the distillation conditions normally applied is presented in Table 1.

TABLE 1

DISTILLATION PROCEDURES FOR PURIFICATION OF SOLVENTS

Solvent	Grade	Drying Agent	Column	Condition
PC	Practical	CaH_2	Spinning Band	5 to 10 mm Hg; reflux ratio: 30/1
DMF	Spectro quality	Multirathane ¹	Spinning Band (or Vigreux)	25 mm Hg; reflux ratio: 10/1
AN	Reagent	P_2O_5	Spinning Band	Atmospheric pressure; dry nitrogen; reflux ratio: 25/1

The solvents are usually purified in batches of approximately 500 milliliters. The vapor phase chromatographic analysis method used for routine characterization of the solvents is subsequently described. The analysis results of the individual solvent batches used during the program are presented in Table 2. The water content of the distilled product is normally between 20 and 50 ppm. A content of organic impurities between 0 and 40 ppm is normally found by the vapor phase chromatographic analysis on a Porapak Q column.



TABLE 2

CHARACTERIZATION OF DISTILLED SOLVENT BATCHES

Solvent Code	H ₂ O Content, ppm	Organics, ppm
PC #2-2	55	20
PC #2-3	25	None*
PC #2-4	20	15
PC #2-5	20	35
PC #2-6	35	None
DMF #1-2	20	140
DMF #3-2	40	None
DMF #4-2	100	None
DMF #3-3	45	35
AN #1-2	40	None
AN #3-1	50	None

*No organic impurity at a level of 10 ppm or greater was detected in the analysis.

Analysis of Acetonitrile by Vapor PhaseChromatography

Two samples of AN, AN #1-2 and AN #3-1, have been completely characterized by vapor phase chromatography. Three columns were employed to detect various species as outlined in Table 3.



TABLE 3

COLUMNS EMPLOYED IN THE CHARACTERIZATION OF ACETONITRILE

Column*	Temperature, C	Detector	Species Characterized
Porapak Q	150	Cross section	Water
Apiezon L	40	Flame ionization	Lower boiling materials
Apiezon L	100	Flame ionization	Higher boiling materials
Carbowax 20M	40	Flame ionization	Lower boiling materials
Carbowax 20M	100	Flame ionization	Higher boiling materials
Porapak Q	140	Flame ionization	Acrylonitrile and very volatile materials

*Hydrogen was used as the carrier gas, its flow rate was 25 cc/min

A sample of AN containing 120 ppm water was analyzed with a Porapak Q column; a chromatogram is presented in Fig. 1. Water is not completely separated from AN under the conditions utilized **for** the determination of water in PC and DMF. More complete separation can be obtained by decreasing either the column temperature or the sample size. Decreasing the column temperature causes the water peak to tail; decreasing the sample size decreases the amount of water being determined.

Under the experimental conditions employed, the water peak tails somewhat and does not return to the baseline before the initial portion **of** the AN peak. However, the water peak can be extrapolated to the baseline and its area measured. Under these conditions, the optimum sensitivity is obtained.




Figure 1. Initial Portion of Chromatogram of Acetonitrile Containing 120 ppm Water



Known amounts of water were added to a sample of AN and the areas of the resulting water peaks were measured. The area of the water peak for various additions of water is presented in Table 4. The response for water is 112 ppm/cm^2 .

TABLE 4

AREA OF WATER PEAK FOR SOLUTIONS OF ACETONITRILE
CONTAINING VARIOUS AMOUNTS OF WATER

<u>H₂O added, ppm</u>	<u>H₂O peak area, cm²</u>
0*	1.1
196	3.0
408	4.9
645	6.7
1130	10.8

*The AN to which the water was added contained some water. Based on the response of 112 ppm/cm^2 , the AN contained 120 ppm water.

This response corresponds to $8.7 \text{ micrograms H}_2\text{O/cm}^2$. This value is greater than the responses found for PC (6.0) and DMF (6.4). The difference is probably caused by the fact that the extrapolation of the water peak did not include all of the peak area under the acetonitrile peak. However, the assumed area of the water peak was found to be proportional to the water content of the AN and can be used to determine the water concentration in AN samples. The lower limit for the determination of water in AN appears to be 10 ppm.



Three columns were used for the characterization of organic impurities in AN. Carbowax 20M and Apiezon L columns were used for the reasons discussed in a previous report (Ref. 2) under the characterization of DMF. A third column, a 6-foot Porapak Q column, was used to determine acrylonitrile and other possible volatile impurities in AN. The latter column gives an excellent separation of AN and acrylonitrile. The retention times at 140 C of AN and acrylonitrile are 6.5 and 10.5 minutes, respectively. This separation is important because acrylonitrile is usually found as an impurity in AN. Furthermore, since AN is eluted very rapidly from the Apiezon L and Carbowax 20M columns, good separation between AN and any volatile impurities may not occur. Because AN is not eluted as rapidly on Porapak Q, volatile impurities should be separated.

Some chromatograms of purified AN are presented in Fig. 2 through 4; the chromatograms obtained with AN #3-1 were virtually identical. Two additional chromatograms were run at 100 C on the Carbowax 20M and Apiezon L columns. Each chromatogram was recorded for 60 minutes to allow any higher boiling impurities to be eluted. No peaks were evident on any of the chromatograms.

If an impurity were present at the 100 ppm level, a peak approximately one-fifth the size of the AN should be observed on the chromatogram at the X0.2 attenuation. Because no such peak appeared, there are no impurities in the AN with concentrations greater than 100 ppm.




Figure 2 . Chromatogram of Acetonitrile, AN #1-2, on Apiezon L




Figure 3. Chromatogram of Acetonitrile, AN #1-2, on Carbowax 20M




Figure 4. Chromatogram of Acetonitrile, AN #1-2, on Porapak Q

Routine Characterization of Distilled Solvents

Vapor phase chromatographic procedures for the determination of water and organic impurities in all three solvents (PC, DMF, and AN) have been developed. Table 5 presents the experimental parameters for the routine analysis applied to monitor the quality of the distilled solvents.

TABLE 5

EXPERIMENTAL PARAMETERS AND RESPONSE FOR THE ROUTINE DETERMINATION OF WATER IN **PROPYLENE** CARBONATE, **DIMETHYL** FORMAMIDE, AND ACETONITRILE

Conditions*	Solvent		
	PC	DMF	AN
Sample Size, microliters	100	100	100
Column Dimension	3/16 inch by 6 feet	3/16 inch by 6 feet	3/16 inch by 6 feet
Column Packing	Porapak Q	Porapak Q	Porapak Q
Column Temperature, C	165	165	150
Injector Temperature, C	175	175	175
Carrier Gas	Hydrogen	Hydrogen	Hydrogen
Flowrate, cc/min	25	25	25
Detector	Cross Section	Cross Section	Cross Section
Detector Temperature, C	165	165	165
Response (by weight), ppm/cm ²	50	67	112
Response, microgramsH ₂ O/cm ²	6.0	6.4	8.7

*Chromatograph: Aerograph 660, Wilkens Instrument & Research, Inc.
Recorder: Leeds & Northrup Speedomax G; 750 microvolts full scale,
1/2 inch per minute



This routine analysis does not constitute a complete characterization but furnishes data in regard to the most important impurity, water, as well as the most likely organic impurities. The lower limit for the quantitative determination of water is approximately 5 ppm in PC and in DMF, and 10 ppm in AN.

NUCLEAR MAGNETIC RESONANCE STRUCTURAL STUDIES

TMA·PF₆* and TMA·F** in Propylene Carbonate and Dimethyl Formamide

It is expected that dissolving TMA·PF₆ and TMA·F would result in the formation of (TMA)⁺ and (PF₆)⁻ and F⁻ ions, respectively. To verify this, both the F¹⁹ resonance and H¹ resonance were investigated in PC and DMF solution containing these solutes; the solutions were identical to the diluted solutions used for solubility determinations (Table 8). The F¹⁹ resonance in both PC and DMF containing TMA·PF₆ is an equal intensity doublet. No other lines were observed. Because P has a spin of 1/2, spin-spin interaction should lead to an equal intensity doublet. Furthermore, all F¹⁹ in (PF₆)⁻ are chemically equivalent; therefore, complex spectra would be only due to spin-spin interactions. Thus, the finding of only an equal intensity doublet is consistent with the assumption that the ion containing F¹⁹ is the (PF₆)⁻ ion.

Because of the relatively low solubility, these lines were rather weak. The even lower solubility of TMA·F in PC and DMF and the smaller number of fluorine atoms per solute anion resulted in no F¹⁹ line being observed for these solutions.

*TMA·PF₆ = tetramethylammonium hexafluorophosphate
**TMA·F = tetramethylammonium fluoride



In contrast, the proton line due to the addition of $\text{TMA} \cdot \text{PF}_6$ and $\text{TMA} \cdot \text{F}$ was observed in all solutions. It should be noted that $\text{TMA} \cdot \text{F}$ contains the same number of protons as $\text{TMA} \cdot \text{PF}_6$. Therefore, the low solubility of $\text{TMA} \cdot \text{F}$ did not prevent the proton resonance line from being observed as was the case with F^{19} resonance. In all cases the H^1 line consisted of an equal intensity triplet with a splitting of less than 1 Hz as shown in Fig. 5. The H^1 resonance has been observed for NH_3 (Ref. 3) and consists of an equal intensity triplet with the splitting of 46 ± 2 Hz between adjacent lines. This pattern is explained on the basis that all H^1 are equivalent and split into a triplet by virtue of a spin-spin interaction with N^{14} which has a spin of 1. By analogy, because all H^1 are equivalent in a $(\text{TMA})^+$ ion and because interaction with N^{14} would yield a triplet as observed, the observations are consistent with what is expected for a $(\text{TMA})^+$ ion. The splitting is much less for $(\text{TMA})^+$ than for NH_3 because the splitting must bridge another bond due to the carbon in the methyl groups.

AlCl_3 in Dimethyl Formamide

To date, the nuclear magnetic resonance structural studies based upon observation of resonance patterns of the solvent have been concentrated on observations in DMF containing AlCl_3 . The H^1 spectrum of pure DMF (Fig. 6) is relatively simple. However, under closer scrutiny the spectrum due to the methyl protons is more complex. Effort has been focused on AlCl_3 in DMF because of the observation of displacement of the H^1 lines by coordination with AlCl_3 . This has been previously reported by Fratiello et al. (Ref. 4). A spectrum of DMF containing 0.0528 M AlCl_3 is shown in Fig. 7. The downfield shift of the aldehyde proton is greater than that of the methyl protons. Furthermore, the




Figure 5 . H^1 Spectrum for $(TMA)^+$




Figure 6. H1 Spectrum for Pure DMF




Figure 7. H^1 spectrum for 0.0528 M AlCl_3/DMF



methyl protons are not shifted the same amount. These shifts have been measured and the results, 51.8 Hz for the aldehyde proton and 25.5 Hz and 21.2 Hz for the methyl protons, are in general agreement with the results of Ref. 4. The interpretation of these results, presented in Ref. 4, is that AlCl_3 coordinates the DMF molecules at the oxygen site rather than the nitrogen site.

The H^1 resonance pattern obtained from DMF containing 1 M LiCl is the same as for pure DMF. No downfield peaks are observed. Thus, either LiCl does not coordinate, or the effect upon the electron structure is too small to be observed. Furthermore, the H^1 resonance pattern in DMF containing both 0.0528 M AlCl_3 and 0.0528 M LiCl is the same as that found in 0.0528 M AlCl_3/DMF .

More detailed study of the methyl doublet in DMF revealed that each peak of the doublet is itself a doublet as shown in Fig. 8. The complete methyl proton spectrum of 0.0528 AlCl_3/DMF is shown in Fig. 9. The secondary splitting is 0.63 Hz in both pure DMF and the uncoordinated DMF in 0.0528 M AlCl_3/DMF . However, the splitting in the coordinated DMF is 0.85 Hz. This difference has not yet been completely interpreted. The splitting is probably due to spin-spin interaction with the aldehyde proton. When the DMF is coordinated, the chemical environment of the methyl locations is altered as is shown by the fact that each line of the methyl doublet is shifted downfield. It is, therefore, reasonable to expect that the spin-spin coupling in the coordinated DMF is different from the uncoordinated DMF.

The ratio of the intensity of the coordinated DMF peaks to the uncoordinated DMF peaks is a measure of the coordination number. In an attempt to determine how many moles of DMF are coordinated by 1 mole of AlCl_3 , the




Figure 8. H^1 Spectra, Methyl Doublet at High Resolution, in Pure DMR,




Figure 9. H^1 Spectrum of Methyl Protons in 0.0528 M $AlCl_3/DMF$



areas of the uncoordinated lines were compared with the areas of the coordinated DMF lines. This comparison is subject to rather large errors because the coordinated lines are relatively weak and a greater fraction of the signal is lost in the noise. This would lead to an underestimate of the coordination number. The area comparison yields a coordination number of approximately 4 assuming a one to one correspondence of the amount of AlCl_3 dissolved in solution to the coordinated peak intensity. Because of the errors involved, this is interpreted as showing that the coordination number is greater than 4. Judging from the line intensity, the error can not be as high as 100 percent; therefore, the coordination number must be less than 8. Thus, the results suggest the most likely coordination number to be 6, which is not an unreasonable result.

PHYSICAL PROPERTY DETERMINATIONS

Viscosity Measurements

The results of viscosity measurements made during this report period are presented in Table 6. The experimental procedure was described previously (Ref. 2). The solutions were prepared in a dry box and brought to temperature equilibrium while enclosed in a volumetric flask with a polyethylene bag containing dry nitrogen as an additional protective seal (for saturated solutions the handling procedure was the same as described in the Solubility Measurements section). The solutions were exposed to the atmosphere only while viscosity and density measurements were being made.

The densities necessary for these determination were measured using a Christian Becker Chainomatic Density Balance. This instrument allows rapid and accurate measurements of densities to three decimal points.



TABLE 6

VISCOSITY DETERMINATIONS AT 25 C

Solute	Concentration	Solvent	Density, gm/cc	Viscosity, millipoise
None		PC #2-6	1.203	24.8
None		AN #1-2	0.777	3.36
AlCl_3 #3*	1.03 M	PC #2-6	1.257	57.2
LiCl #2 + AlCl_3 #3	Saturated 1.03 M	PC #2-6	1.257	71.6
AlCl_3 #3 + LiCl #2	Saturated 1.00 M	DMF #3-2	0.984	22.8
$\text{TMA} \cdot \text{PF}_6$ #1	Saturated	PC #2-4	1.209	26.6
$\text{TMA} \cdot \text{PF}_6$ #1	Saturated	DMF #4-2	0.964	8.99
$\text{TMA} \cdot \text{PF}_6$ #1	Saturated	AN #1-2	0.787	3.57

*All solutions of AlCl_3/PC and $\text{LiCl}+\text{AlCl}_3/\text{PC}$ have a brownish tinge when prepared very slowly with stirring.



For example, the density of pure PC obtained by the pycnometer technique was 1.200 gm/ml, while the density obtained with the density balance was 1.203. This accuracy is entirely adequate for viscosity measurements.

Solubility Measurements

The results of solubility measurements made during this report period are presented in Table 7. Saturated solutions were prepared in a dry box by adding an excess of salt to the solvent of interest. The flasks were then sealed with a glass stopper and the neck of the flask enclosed in a polyethylene bag containing dry nitrogen. The flasks were removed from the dry box and placed in an 80 C bath for several hours and then allowed to equilibrate in the constant temperature baths at 25 and 60 C, respectively, for several days.

In general, the solubilities of the chlorides were determined by dilution of 10-cc samples of saturated solution with distilled water and titrating with standard AgNO_3 .

The lithium fluoride solutions were analyzed for lithium content by atomic absorption spectroscopy. The procedure consisted of diluting the saturated solution with solvent and comparing its atomic absorption spectra with calibration curves obtained with known solutions of LiCl or LiClO_4 in the corresponding solvent. No response indicating lithium was obtained with LiF/PC ; the lowest detectable value was estimated to be 5×10^{-6} molar. This value is lower than the values of 6×10^{-5} molar (Ref. 5) and 2×10^{-5} molar (Ref. 1) which were estimated from conductivity data.



TABLE 7

SOLUBILITY DETERMINATIONS

Solute	Solvent	Temperature, °C	Procedure	Solubility, molar
LiCl #2	PC #2-0	25	Chloride Titration	3.8×10^{-2}
		60	Chloride Titration	3.1×10^{-2}
LiCl #2	1 2 M Al ₂ O ₃ /PC #2-2	25	Chloride Titration	6.6×10^{-1}
		60	Chloride Titration	7.5×10^{-1}
AlCl ₃ #3	1 M LiCl/DMF #1-4	05	Chloride Titration	8.8×10^{-2}
LiCl #2	AN #1-2	25	Chloride Titration	2.55×10^{-2}
		60	Chloride Titration	1.42×10^{-2}
LiF #2	PC #2-4	25	Atomic Absorption	$< 5 \times 10^{-6}$
		60	Atomic Absorption	$< 5 \times 10^{-6}$
LiF #2	DMF #1-2	25	Atomic Absorption	3.18×10^{-5}
		60	Atomic Absorption	5.34×10^{-5}
LiF #2	AN #1-2	25	Atomic Absorption	2.2×10^{-5}
		60	Atomic Absorption	3.2×10^{-5}
TMA•PF ₆ #1	PC #2-4	25	Nuclear Magnetic Resonance	1.5×10^{-1}
		60	Nuclear Magnetic Resonance	2.2×10^{-1}

TABLE 7
(Concluded)

Solute	Solvent	Temperature, C	Procedure	Solubility, molar
MA F ₆ #1	DMF #4-2	25	Nuclear Magnetic Resonance	2.4×10^{-1}
		60	Nuclear Magnetic Resonance	3.6×10^{-1}
TMA F ₆	AN #1-2	25	Evaporation to Dryness	1.0×10^{-1}
		60	Evaporation to Dryness	1.8×10^{-1}
MA #1	P< #2-2	25	Nuclear Magnetic Resonance	6.5×10^{-2}
TMA #1	DMF #4-2	25	Nuclear Magnetic Resonance	2.8×10^{-2}
#2	P< #2-4	25	Chloride Titration	4.9×10^{-3}
		60	Chloride Titration	4.2×10^{-3}
#2	DMF #1-2	25	Chloride Titration	1.30
		60	Chloride Titration	2.68
#2	1 M LiCl/DMF #4-2	25	Chloride Titration	1.04
		60	Chloride Titration	1.34

The F^{19} and H^1 nuclear magnetic resonances were used to determine the amounts of $TMA \cdot PF_6$ and $TMA \cdot F$ dissolved in DMF and PC. Quantitative analyses were obtained by comparing the line intensity from unknown, diluted samples with that from a sample having a known concentration. The results are shown in Table 8. Comparison of the results obtained by F^{19} and H^1 analysis for $(PF_6)^-$ and $(TMA)^+$ (the assignment of ion species is discussed in this report) ions reveals good agreement for $TMA \cdot PF_6$ dissolved in DME. Although the concentrations obtained for $(TMA)^+$ are consistently lower than the results obtained for $(PF_6)^-$ the difference is within the limits of error (Table 8). For $TMA \cdot PF_6$ dissolved in PC, the agreement is within the limits of error for the saturated solution at 25 C sample but not for the saturated solution at 60 C sample. The source of this discrepancy is not known. Again the concentrations determined by H^1 analysis are consistently lower than those determined by F^{19} analysis. Because the H^1 lines are more complex than the F^{19} lines, more confidence should be credited to the F^{19} analyses.

In the case of $TMA \cdot PF_6/AN$, preliminary results were obtained by evaporation of 10-cc samples to dryness and weighing the dried salt. These results will be compared with those obtained by nuclear magnetic resonance procedures.

Conductance Measurements

Conductivity values of solutions were determined in Freas cells as described previously (Ref, 1). The conductivity measurements taken during this report period are summarized in Table 9 and are discussed on the following pages.

Results obtained with electrolytes containing $LiCl$ and/or $AlCl_3$ in PC are presented in Tables 10 through 13 and Fig. 10 through 14. In the



TABLE 8

SOLUTE CONCENTRATIONS DETERMINED BY
NUCLEAR MAGNETIC RESONANCE

Solvent	Solute	Dilution"	Ion	Concentration of Saturated Solutions, molar
DMF #4-2	TMA•PF ₆ (0.101 M)		(PF ₆) ⁻	
	TMA•PF ₆ (Saturated at 25 C)	1:1	(PF ₆) ⁻	0.262 ±0.018
	TMA•PF ₆ (Saturated at 60 C)	5: 1	(PF ₆) ⁻	0.379 ±0.030
PC #2-4	TMA•PF ₆ (0.0994 M)		(PF ₆) ⁻	
	TMA•PF ₆ (Saturated at 25 C)	1:1	(PF ₆) ⁻	0.152 ±0.013
	TMA•PF ₆ (Saturated at 60 C)	4: 1	(PF ₆) ⁻	0.234 ±0.025
DMF #4-2	TMA•PF ₆ (0.101 M)		(TMA) ⁺	
	TMA•PF ₆ (Saturated at 25 C)	1:1	(TMA) ⁺	0.223 ±0.025
	TMA•PF ₆ (Saturated at 60 C)	5: 1	(TMA) ⁺	0.337 ±0.034
PC #2-4	TMA•PF ₆ (0.0994 M)		(TMA) ⁺	
	TMA•PF ₆ (Saturated at 25 C)	1:1	(TMA) ⁺	0.142 ±0.015
	TMA•PF ₆ (Saturated at 60 C)	4: 1	(TMA) ⁺	0.176 ±0.020

*Saturated solutions were diluted with pure solvent and the concentrations of such solutions were determined.

TABLE 8
(Concluded)

Solvent	Solute	Dilution*	Ion	concentration of Saturated Solutions, molar
DMF #4-2	TMA ⁺ F ⁻ (Saturated at 25 C)	1:1	(TMA) ⁺	0.028 ±0.005
PC #2-3	TMA ⁺ F ⁻ (Saturated at 25 C)	1:1	(TMA) ⁺	0.065 ±0.010

*Saturated solutions were diluted with pure solvent and the concentrations of such solutions were determined.

TABLE 9

SUMMARY OF CONDUCTANCE MEASUREMENTS

Solutes	Concentration	Solvent	$\lambda^* (25^\circ \text{C}),$ $\text{ohm}^{-1} \text{cm}^{-1}$	$\lambda (60^\circ \text{C}),$ $\text{ohm}^{-1} \text{cm}^{-1}$
LiCl #2-1	Dilution series	PC #2-2		
LiCl #2-1	Saturated	PC #2-2		
AlCl ₃ #3	Dilution series	PC #2-3		
AlCl ₃ #3	Dilution series	PC #2-5		
LiCl #2-1 + AlCl ₃ #3	Dilution series	PC #2-5		
LiCl and/or AlCl ₃	Dilution series	DMF		
LiCl #2-1	0.0528 M	DMF #3-2	1.97×10^{-3}	2.48×10^{-3}
LiCl #2-1 + AlCl ₃ #3	0.0528 M 0.0528 M	DMF #3-2	3.79×10^{-3}	2.95×10^{-3}
LiCl #2-1 + AlCl ₃ #3	1 M Saturated	DMF #3-2	7.77×10^{-3}	1.19×10^{-2}
TMA•PF ₆ #1	Dilution series	PC #2-5		
TMA•PF ₆ #1	Saturated	PC #2-5	2.71×10^{-3}	6.75×10^{-3}
TMA•PF ₆ #1	Dilution series	DMF #1-2		
TMA•PF ₆ #1	Saturated	DMF #1-2	1.11×10^{-2}	1.93×10^{-2}
TMA•PF ₆ #1	Dilution series	AN #1-2		
TMA•PF ₆ #1	Saturated	AN #1-2	1.14×10^{-2}	2.26×10^{-2}
CuCl ₂ #2	Saturated	DMF #1-2	5.95×10^{-3}	9.06×10^{-3}

* λ : Specific conductance



TABLE 10

SPECIFIC CONDUCTANCE (λ) AND EQUIVALENT CONDUCTANCE (Λ)
OF LiCl/PC AT 25 AND 60 C

Concentration (C), molar	\sqrt{C} , 1/2 molar	λ (25 C), ohm ⁻¹ cm ⁻¹	Λ^{∞} (25 C), ohm ⁻¹ equ ⁻¹ cm ²	λ (60 C), ohm ⁻¹ cm ⁻¹	Λ^* (60 C), ohm ⁻¹ equ ⁻¹ cm ²
0.0065	0.163	1.459×10^{-4}	5.49	2.719×10^{-4}	10.2
0.0553	0.0728	5.828×10^{-5}	10.9	1.079×10^{-4}	20.2
0.0265	0.0515	3.600×10^{-5}	13.5	6.717×10^{-5}	25.0
0.0106	0.0326	1.825×10^{-5}	16.9	3.439×10^{-5}	31.6
0.00530	0.0230	1.075×10^{-5}	19.7	2.011×10^{-5}	36.3
0.001766	0.0133	4.261×10^{-6}	22.5	7.769×10^{-6}	39.0
0		2.858×10^{-7}	Extrapolated: $\Lambda_0 = 26.2$	8.846×10^{-7}	Extrapolated: $\Lambda_0 = 44.9$

* Λ : Equivalent conductance, corrected for conductance of pure solvent



TABLE 11

SP-4114 CONDUCTANCE (λ) AND EQUIVALENT CO
OF AlCl_3/PC AT 25 AND 60 C

Concentration (C), molar	\sqrt{C} , $1/2$ molar	$\lambda(25\text{ C})$, $\text{ohm}^{-1}\text{cm}^{-1}$	$\Lambda^*(25\text{ C})$, $\text{ohm}^{-1}\text{equ}^{-1}\text{cm}^2$	$\lambda(60\text{ C})$, $\text{ohm}^{-1}\text{cm}^{-1}$	$\Lambda^*(60\text{ C})$, $\text{ohm}^{-1}\text{equ}^{-1}\text{cm}^2$
0.00	0.00	6.960×10^{-3}	6.96	1.309×10^{-2}	13.09
0.001	0.0316	3.227×10^{-3}	12.36	5.567×10^{-3}	21.33
0.0022	0.047	8.218×10^{-4}	15.73	1.390×10^{-3}	26.62
0.0044	0.066	1.716×10^{-4}	16.42	2.838×10^{-4}	27.16
0.00522	0.0722	7.618×10^{-5}	14.56	1.275×10^{-4}	24.37
0.0021	0.05108	3.110×10^{-5}	11.85	5.576×10^{-5}	21.24
0.00130	0.03605	1.416×10^{-5}	10.75	2.538×10^{-5}	19.28
0.000522	0.02285	5.421×10^{-6}	10.04	9.636×10^{-6}	17.85
0.00124	0.0114	1.351×10^{-8}	9.46	2.291×10^{-6}	15.91
0		1.784×10^{-7}		3.185×10^{-7}	

* Λ : Equivalent conductance, corrected for conductance of pure solvent



TABLE 12

SPECIFIC CONDUCTANCE (λ) AND EQUIVALENT CONDUCTANCE (Λ)
OF AlCl_3/PC AT 25 AND 60 C

Concentration (C), molar	\sqrt{C} , $1/2$ molar	λ (25 C), $\text{ohm}^{-1} \text{cm}^{-1}$	Λ^* (25 C), $\text{ohm}^{-1} \text{equ}^{-1} \text{cm}^2$	λ (60 C), $\text{ohm}^{-1} \text{cm}^{-1}$	Λ^* (60 C), $\text{ohm}^{-1} \text{equ}^{-1} \text{cm}^2$
0.0913	0.302	1.356×10^{-3}	14.8	2.300×10^{-3}	25.2
0.0183	0.135	2.883×10^{-4}	15.7	4.767×10^{-4}	26.0
0.00913	0.0955	1.307×10^{-4}	14.2	2.111×10^{-4}	23.0
0.00456	0.0676	4.992×10^{-5}	10.8	8.853×10^{-5}	19.1
0.00228	0.0478	2.077×10^{-5}	8.83	3.853×10^{-5}	16.4
0.00114	0.0338	1.161×10^{-5}	9.62	2.074×10^{-5}	17.2
0.000570	0.0239	6.807×10^{-6}	10.8	1.340×10^{-5}	21.5
0.000285	0.0169	6.682×10^{-6}	21.2	1.330×10^{-5}	42.66
0.000143	0.0119	5.576×10^{-6}	34.6	1.104×10^{-5}	69.23
0		6.289×10^{-7}		1.136×10^{-6}	

Λ^* Equivalent conductance, corrected for conductance of solvent



TABLE 13

SPECIFIC CONDUCTANCE (λ) AND EQUIVALENT CONDUCTANCE (Λ)
OF LiCl+AlCl₃/PC AT 25 AND 60 C

Concentration (molar)*	\sqrt{C} , molar ^{1/2}	λ (25 C), ohm ⁻¹ cm ⁻¹	Λ^{**} (25 C), ohm ⁻¹ cm ²	λ (60 C), ohm ⁻¹ cm ⁻¹	Λ^{**} (60 C), ohm ⁻¹ cm ²
1.00*	1.00	6.578 x 10 ⁻³	6.58	1.292 x 10 ⁻²	12.9
0.200	0.447	3.003 x 10 ⁻³	15.0	5.188 x 10 ⁻³	25.9
0.0400	0.200	7.515 x 10 ⁻⁴	18.8	1.270 x 10 ⁻³	31.8
0.00400	0.0632	8.595 x 10 ⁻⁵	21.5	1.449 x 10 ⁻⁴	36.2
0.00200	0.0447	4.480 x 10 ⁻⁵	22.3	7.521 x 10 ⁻⁵	37.4
0.00100	0.0316	2.354 x 10 ⁻⁵	23.4	3.929 x 10 ⁻⁵	39.0
0.000500	0.0224	1.232 x 10 ⁻⁵	24.3	2.068 x 10 ⁻⁵	40.8
0.000250	0.0158	6.814 x 10 ⁻⁶	26.6	1.158 x 10 ⁻⁵	44.9
0.000125	0.0112	3.788 x 10 ⁻⁶	28.9	6.509 x 10 ⁻⁶	49.7
0		1.752 x 10 ⁻⁷	Extrapolated: $\Lambda_o = 34.5$	2.988 x 10 ⁻⁷	Extrapolated: $\Lambda_o = 61.7$

*The initial solution was 1 molar with respect to AlCl₃ and saturated with respect to LiCl (0.78 molar LiCl). The other solutions were obtained by diluting this solution. The concentrations listed refer to the AlCl₃ concentration.

** Λ : Equivalent conductance, corrected for conductance of pure solvent




Figure 10. Equivalent Conductance of LiCl in Propylene Carbonate at 25 and 60 C




Figure 11. Equivalent Conductance of LiCl in Propylene Carbonate at 25 and 60 C




Figure 12. Equivalent (Molar) Conductance of AlCl_3 in Propylene Carbonate at 25 and 60 C




Figure 13. Equivalent (Molar) Conductance of $\text{LiCl} + \text{AlCl}_3$ in Propylene Carbonate at 25 and 60°C





Figure 14. Comparison of Equivalent (Molar) Conductances of Electrolytes Containing LiCl and/or AlCl_3 in PC at 25 and 60 C

case of LiCl/PC (Fig. 10 and 11) Λ plotted vs \sqrt{C} results in a straight line at low concentrations, and an extrapolation to zero concentration is readily obtained: $\Lambda_o = 26.2 \text{ ohm}^{-1} \text{ equ}^{-1} \text{ cm}^2$ at 25 C and $\Lambda_o = 44.9 \text{ ohm}^{-1} \text{ equ}^{-1} \text{ cm}^2$ at 60 C. For the AlCl_3/PC system, two sets of measurements were taken in addition to the results reported earlier (Ref. 1). In the first set (Table 11), the dilution series was initiated with a 1 molar solution which was brownishly discolored; in the second set (Table 12), the dilution was initiated with a 0.1 molar solution which was only slightly tinted. A maximum and a minimum of the equivalent conductance was observed for AlCl_3/PC with decreasing solute concentration (Fig. 12), although in one case the minimum was only fragmentally indicated as a slight change in the slope of the curve. An unambiguous interpretation of this behavior has not been found; the occurrence of the minimum at low concentrations may be connected with the water content of the solvent, which was approximately 20 ppm (corresponding to a concentration of 0.001 molar). A study of this effect as a function of the water content could result in clarification, but such a study is beyond the scope of the present work. A reasonable extrapolation of the equivalent conductance to zero concentration cannot be made from the present measurements. For the electrolyte containing LiCl and AlCl_3 , Λ_o of 34.5 and 61.7 $\text{ohm}^{-1} \text{ equ}^{-1} \text{ cm}^2$ have been obtained at 25 and 60 C, respectively, but the extrapolation is somewhat uncertain.

A comparison of the three electrolytes is illustrated in Fig. 14. There appears to be an additive effect in the molar conductances when LiCl is added to AlCl_3/PC . At low concentrations, the high conductance of LiCl/PC predominates; at higher concentrations, the conductance curves of AlCl_3/PC and of the mixed electrolyte approach each other because the contribution of LiCl becomes small. A chemical interaction resulting in the formation of new species as indicated by the increase of the solubility of LiCl is not readily evidenced by the present conductance results. Nuclear magnetic resonance studies may produce more direct, less ambiguous information in this respect.



It has been found previously (Ref. 2) that the sum of the Λ_o values for LiCl/DMF and AlCl₃/DMF electrolytes **did** not equal the Λ_o value obtained for the LiCl + AlCl₃/DMF mixed electrolyte. Some of the extrapolations to zero concentration were questionable because linearity at low concentrations was not obtained. Therefore, equivalent conductance values are compared at a specific concentration, 0.05 molar. The values on which the comparison is based are presented in Table 14. The majority of the values were obtained by **interpolation of** conductance curves. In the case of LiCl/PC, an extrapolation was made, because 0.05 molar designates a concentration beyond the solubility of LiCl in PC. The sum of the Λ values for a 0.0528 M LiCl/DMF and a 0.0528 M AlCl₃/DMF solution is $37.4 + 53 = 90.4 \text{ ohm}^{-1} \text{ equ}^{-1} \text{ cm}^2$, but the Λ value for a 0.0528 M LiCl + 0.0528 M AlCl₃/DMF solution is $71.8 \text{ ohm}^{-1} \text{ equ}^{-1} \text{ cm}^2$. However, this latter solution is expected to have a higher ionic strength, and one should rather take into account the Λ values at 0.106 molar; if it is assumed that the two solutes do not chemically interact, some interaction will be reflected nevertheless in a change of the activity of the individual components. If as a first approximation, the Λ values of 0.106 M LiCl/DMF and of 0.106 M AlCl₃/DMF are added, $74 \text{ ohm}^{-1} \text{ equ}^{-1} \text{ cm}^2$ results, which closely approximates the value for the 0.0528 M LiCl + 0.0528 M AlCl₃/DMF mixture ($\Lambda = 71.8 \text{ ohm}^{-1} \text{ equ}^{-1} \text{ cm}^2$ at 25 C), and a similar agreement is found also for values obtained at 60 C. This result gives no indication of any interaction between the two solutes, LiCl and AlCl₃, such as:



This appears to apply also for values obtained in PC, although the extrapolation of Λ values for LiCl/PC is uncertain. Because a 1 M AlCl₃/PC solution saturated with LiCl (~ 0.8 molar) was used for the dilution series, the Λ values of 0.09 molar LiCl/PC and AlCl₃/PC solutions



TABLE 14

COMPARISON OF CONDUCTANCE VALUES OF 0.05 M LiCl,
0.05 M AlCl₃, AND 0.05 M LiCl + 0.05 M AlCl₃
SOLUTIONS IN PC AND DMF

Solution	Concentration, molar	Λ^* (25 C), $\text{ohm}^{-1} \text{equ cm}^2$	Λ^* (60 C), $\text{ohm}^{-1} \text{equ cm}^2$	Determination
LiCl/PC	0.04	4.2	8.0	(e)
	0.09	2.2	4.2	(e)
	0	26.2	44.9	(e)
AlCl ₃ /PC	0.05	15.8	26.8	(i)
	0.09	14.8	25.3	(i)
LiCl + AlCl ₃ /PC	0.04 + 0.05	18.4	31.0	(i)
	0	34.5	61.7	(e)
LiCl/DMF	0.0528	37.4	46.9	(m)
	0.106	31	38	(i)
	0	84.0	118	(e)
AlCl ₃ /DMF	0.0528	53	71	(i)
	0.106	43	58	(e)
	0	220	280	(e)
LiCl + AlCl ₃ /DMF	0.0528 + 0.0528	71.8	93.7	(m)
	0	260	325	(e)

* Λ : Equivalent (molar) conductance, corrected for conductance of pure solvent
NOTE: m = measured value i = interpolated value e = extrapolated value



at 25 C (2.2 and 14.8 $\text{ohm}^{-1}\text{equ}^{-1}\text{cm}^2$, respectively) were compared with the respective values for 0.04 M LiCl + 0.05 M AlCl_3/PC ($\Lambda = 18.4 \text{ ohm}^{-1}\text{equ}^{-1}\text{cm}^2$ at 25 C. No indication of a direct interaction between LiCl and AlCl_3 in PC can be obtained from the preceding comparison, although absence of such an interaction is certainly not proven,

Specific conductance and equivalent conductance values for electrolytes containing $\text{TMA} \cdot \text{PF}_6$ are presented in Tables 15 through 17 and Fig. 15 through 20. Extrapolation of the equivalent conductance to infinite dilution yielded values which suggest the presence of $\text{TMA} \cdot \text{PF}_6$ as a 1-1 electrolyte forming $(\text{CH}_3)_4\text{N}^+$ and PF_6^- ions in all three solvents. This is in agreement with the results of the nuclear magnetic resonance structural studies.

Measurement of Transference Numbers by the Hittorf Method

The cell designed for these experiments is shown in Fig. 21 and 22. The cell design of Wall, Stent, and Ondrejcin (Ref. 6) was modified to allow easy immersion of the lower parts of the cell into an oil bath. The experiments are performed at room temperature; however, the electrolyte warms under current flow because of the relatively low specific conductance of the electrolytes under study, and performing the experiment at a completely controlled, constant temperature is not possible. It appears that cooling of the lower cell parts in a bath is efficient enough to prevent excessive temperature increases in the cell. Cooling of only the lower parts of the cell also furnishes a stable density distribution in the electrolyte. The three compartments are filled with a total of approximately 90 milliliters of electrolyte and the electrolyte is raised to the desired level by applying suction to the center arm. At the conclusion of the experiment, the stopcock is reopened to separate catholyte and anolyte from the electrolyte contained in the middle compartment. The total loss of solute in the cathode and anode compartment is determined by analysis, and the transference numbers are calculated.

TABLE 15

SPECIFIC CONDUCTANCE (λ) AND EQUIVALENT CONDUCTANCE (Λ)
OF TMA-PF₆/PC AT 25 AND 60 C

Concentration (molar)	\sqrt{c} , molar ^{1/2}	λ (25 C), ohm ⁻¹ cm ⁻¹	Λ^* (25 C), ohm ⁻¹ equ cm ²	λ (60 C), ohm ⁻¹ cm ⁻¹	Λ^* (60 C), ohm ⁻¹ equ cm ²
0.09942	0.315	2.236×10^{-3}	22.48	3.776×10^{-3}	37.97
0.0165	0.129	4.503×10^{-4}	27.09	7.637×10^{-4}	46.03
0.00828	0.0910	2.333×10^{-4}	28.10	3.965×10^{-4}	47.75
0.00414	0.0644	1.212×10^{-4}	29.14	2.056×10^{-4}	49.41
0.00207	0.0439	6.218×10^{-5}	29.77	1.059×10^{-4}	50.69
0.00104	0.0322	3.203×10^{-5}	30.44	5.462×10^{-5}	51.87
0.000518	0.0228	1.690×10^{-5}	31.65	2.876×10^{-5}	53.80
0.000259	0.0161	8.830×10^{-6}	32.14	1.506×10^{-5}	54.69
0.000129	0.0114	4.601×10^{-6}	31.63	7.841×10^{-6}	53.62
0		5.083×10^{-7}		9.030×10^{-7}	
			Extrapolated: $\Lambda_0 = 33.9$	Extrapolated: $\Lambda_0 = 57.6$	

* Λ : Equivalent conductance, corrected for conductance of pure solvent



TABLE 16
SPECIFIC CONDUCTANCE (λ) AND EQUIVALENT CONDUCTANCE (Λ)
OF TMA·PF₆/DMF AT 25 AND 60 C

Concentration (C), molar	\sqrt{C} , molar ^{1/2}	λ (25 C), ohm ⁻¹ cm ⁻¹	Λ^* (25 C), ohm ⁻¹ equ ⁻¹ cm ²	λ (60 C), ohm ⁻¹ cm ⁻¹	Λ^* (60 C), ohm ⁻¹ equ ⁻¹ cm ²
0.1010	0.318	5.760×10^{-3}	57.04	7.806×10^{-3}	77.29
0.0101	0.100	7.466×10^{-4}	73.80	1.028×10^{-3}	101.6
0.00505	0.0710	3.905×10^{-4}	77.06	5.393×10^{-4}	106.4
0.00252	0.0502	2.040×10^{-4}	80.27	2.826×10^{-4}	111.2
0.00126	0.0355	1.059×10^{-4}	82.80	1.467×10^{-4}	114.7
0.000631	0.0251	5.479×10^{-5}	84.66	7.622×10^{-5}	117.8
0.000315	0.0177	2.866×10^{-5}	86.60	3.975×10^{-5}	120.3
0.000158	0.0126	1.505×10^{-5}	86.58	2.084×10^{-5}	120.1
0		1.375×10^{-6}	Extrapolated: $\Lambda_0 = 90.5$	1.875×10^{-6}	Extrapolated: $\Lambda_0 = 126$

* Λ_0 : Equivalent conductance, corrected for conductance of pure solvent

TABLE 17

SPECIFIC CONDUCTANCE (λ) AND EQUIVALENT CONDUCTANCE (Λ)
OF TMA·PF₆/AN AT 25 AND 60 °C

Concentration (C), molar	\sqrt{C} , 1/ \sqrt{C} molar ^{1/2}	λ (25 °C), ohm ⁻¹ cm ⁻¹	Λ^* (25 °C), ohm ⁻¹ equ ⁻¹ cm ²	λ (60 °C), ohm ⁻¹ cm ⁻¹	Λ^* (60 °C), ohm ⁻¹ equ ⁻¹ cm ²
0.07097	0.266	8.648 x 10 ⁻³	121.8	1.070 x 10 ⁻²	152.0
0.007097	0.0842	2.180 x 10 ⁻³	306.9	2.733 x 10 ⁻³	385.5
0.003548	0.0596	1.161 x 10 ⁻³	326.7	1.463 x 10 ⁻³	411.8
0.001774	0.0421	6.121 x 10 ⁻⁴	344.1	7.726 x 10 ⁻⁴	434.5
0.000888	0.0296	3.181 x 10 ⁻⁴	356.4	4.030 x 10 ⁻⁴	451.8
0.000444	0.0219	1.652 x 10 ⁻⁴	368.5	2.085 x 10 ⁻⁴	465.5
0.000222	0.0149	8.571 x 10 ⁻⁵	378.7	1.076 x 10 ⁻⁴	476.6
0.000111	0.0105	4.396 x 10 ⁻⁵	381.3	5.450 x 10 ⁻⁵	474.4
0		1.645 x 10 ⁻⁶	Extrapolated: $\Lambda_0 = 402$	1.844 x 10 ⁻⁶	Extrapolated: $\Lambda_0 = 503$

Λ_0 : Equivalent conductance, corrected for conductance of pure solvent




Figure 15. Equivalent Conductance of $\text{TMA} \cdot \text{PF}_6$ in PC at 25 and 60 °C




Figure 16. Equivalent Conductance of $\text{TMA} \cdot \text{PF}_6$ in PC at 25 and 60 C




Figure 17. Equivalent Conductance of $\text{TMA} \cdot \text{PF}_6$ in DMF at 25 and 60 C




Figure 18. Equivalent Conductance of $\text{TMA} \cdot \text{PF}_6$ in DMF at 25 and 60 C




Figure 19. Equivalent Conductance of $\text{TMA} \cdot \text{PF}_6$ in AN at 25 and 60 C




Figure 20. Equivalent Conductance of TMA·PF₆ in AN at 25 and 60 C





Figure 21. Hittorf Cell Schematic



5AL21-3/16/67-C1B

Figure 22. Hittorf Cell



LiCl/DMF was the first system investigated. The experimental conditions and results are summarized in Table 18. A silver sheet anode was used. According to weight loss determinations, the anodic dissolution of the silver was quantitative, silver chloride being soluble in the electrolyte (it appears that this anodic reaction could be recommended for use in a coulometer). When the samples were diluted with water, AgCl precipitated quantitatively. Nickel screen cathodes were used, except in one case (run No. 4) where a copper sheet cathode was substituted. A lithium deposit was observed only in two cases (runs No. 1 and 5). In runs No. 2 through 4 a reaction of the solvent appeared to occur exclusively, and the resulting reducing compounds presented difficulties in the chloride analysis. Oxidation of the samples with H_2O_2 improved the reproducibility of the analysis results, but spurious results were still obtained (e.g., $t_{-} > 1$). The nature of the cathodic products and the conditions under which they form were not investigated (a pretreatment of the nickel substrate may be an important factor). If chlorine-containing organic species were formed, the decrease in chloride ion concentration would not result from ion transport alone. For these reasons, some of the transference numbers for the anion determined from the change in catholyte composition (runs No. 2 through 4) appear to be in error. There are two independent determinations of the transference numbers; (1) from changes of catholyte composition and (2) from change of anolyte composition. Unfortunately, the concentration changes of the anolyte (measured after precipitation of AgCl) are relatively small, because $t_{-} > t_{+}$, and the limited accuracy of the analysis leads to a relatively high uncertainty in the transference numbers calculated from anolyte data.

Because of these difficulties and limitations, only the results of runs No. 1 and 5 are considered; t_{+} and t_{-} are corrected to a sum of 1 (Table 18). An accuracy of ± 0.05 is estimated for the transference

TABLE 18
DETERMINATIONS OF TRANSFERENCE NUMBERS (t_+)
OF LiCl IN DMF BY THE HITTORF METHOD

Run No.	Solute	Concentration, molar	Solvent	Cell Current, milliamperes	Electrolysis Duration, hours	t_+ Calculated From Anolyte	t_- Calculated From Catholyte	t_+ Corrected	t_- Corrected
1	LiCl #2-1	1.25	DMF #3-1	10	6	0.27 ^a	0.73 ^b	0.2	0.73
2	LiCl #2-1	1	DMF #3-1	12	9-1/4	0.15	0.82		
3	LiCl #2-1	1	DMF #4-2	15	9	0.15	1.12		
4	LiCl #2-1	1	DMF #3-3	12	8	0.25	1.71		
5	LiCl #2-1	0.1	DMF #4-2	2.2	8	0.24 ^c	0.70 ^d	0.27	0.73

^aAmount of chloride removed from anolyte (after precipitation of AgCl): 0.61×10^{-3} mole

^bAmount of chloride removed from catholyte: 1.64×10^{-3} mole


^cAmount of chloride removed from anolyte (after precipitation of AgCl): 1.6×10^{-4} mole

^dAmount of chloride removed from catholyte: 4.6×10^{-4} mole



numbers for LiCl/DMF, $t_+ = 0.27$ and $t_- = 0.73$; these compare with $t_+ = 0.31$ and $t_- = 0.69$ as calculated from ion mobilities given by Prue and Sherrington (Ref. 7).

A mixed electrolyte containing 0.1 M CuCl_2 and 1 M LiCl in DME was also studied by the Hittorf method. It was found that the silver anode dissolved with coulombic efficiencies greater than 100 percent; an open circuit corrosion of the silver was verified. Because no copper deposit was observed, it may occur as follows:



The anolyte was analyzed for the copper content and an accumulation of copper was found as shown in Table 19. The analysis result of run No. 1 is too low because some copper species seem to have coprecipitated with the silver chloride upon dilution of the samples with water (the silver chloride appeared bluish). For run No. 2, addition of ammonium hydroxide prevented this. Accumulation of copper in the anode compartment indicates the presence of negatively charged copper species in the electrolyte. Assuming a quantitative formation of CuCl_4^{-2} , the electrolyte would have a composition of 1.0 M Li^+ + 0.8 M Cl^- + 0.1 M CuCl_4^{-2} . If it is assumed, furthermore, that CuCl_4^{-2} has twice the ion mobility of Cl^- because of the higher charge, and that the mobility of Li^+ is one-third of that of Cl^- , 27 percent of the current would be transported by the CuCl_4^{-2} . The experimental figure of $n \times 14.6$ percent for the more reliable result of run No. 2 therefore indicates that $n = 2$ and copper chloride is present in the form of CuCl_4^{-2} in LiCl/DMF. The preceding calculation is only a first approximation; the actual situation may be more complex because of ion pair formation, mixtures of various species, etc.



TABLE 19

HITTORF EXPERIMENT WITH AN ELECTROLYTE CONTAINING
1 M LiCl and 0.1 M CuCl₂ in DMF

Run No.	Accumulated Cu in Anolyte, moles	Corresponding Charge ^{***} , coulombs	Total Charge, coulombs	Percentage of Current Transported by Cu Species
1	$2.16 \times 10^{-4}*$	$n \times 20.8$	288	$n \times 7.2$
2	3.92×10^{-4}	$n \times 37.8$	258	$n \times 14.6$

*Coprecipitation occurred during analysis

**n = charge of copper complex



WORK PLANNED FOR NEXT QUARTER

PREPARATION OF ELECTROLYTES

The distillation of solvents will continue. The purity of the distilled products will be checked on a routine basis by chromatography on a Porapak Q column.

The analysis of all major solutes to be used on the program will be completed.

NUCLEAR MAGNETIC RESONANCE STRUCTURAL STUDIES

High resolution nuclear magnetic resonance studies of solvents containing solutes will continue in both $\text{LiCl} + \text{AlCl}_3/\text{PC}$ and $\text{LiCl} + \text{AlCl}_3/\text{AN}$ and will be initiated for solutions of copper halides. The studying of solutes by wide line techniques will be initiated, with AlCl_3 and LiCl in PC and DMF being emphasized. Structural information obtained during these studies will be correlated with the physical and electrochemical properties of the electrolytes.

PHYSICAL PROPERTY DETERMINATIONS

Determinations of physical properties will continue. Solubility studies of lithium fluoride and lithium chloride, as well as of the copper halides in electrolyte solutions will be emphasized. In some cases, the influence of water on these solubilities will be investigated. Other measurements, such as the measurement of sonic velocities and of diffusion coefficients will be initiated.



REFERENCES

1. NASA CR-72106, Properties of Nonaqueous Electrolytes, First Quarterly Report, R. Keller, J. N. Foster, and J. M. Sullivan, Rocketdyne, a Division of North American Aviation, Inc., Canoga Park, California, October 1966.
2. NASA CR-72168 Properties of Nonaqueous Electrolytes, Second Quarterly Report, R. Keller, J. N. Foster, J. D. Ray, and J. Pl. Sullivan, Rocketdyne, a Division of North American Aviation, Inc., Canoga Park, California, January 1967.
3. Ogg, R. A., and J. D. Ray, J. Chem. Phys. 26, 1515 (1957).
4. Fratiello, A., R. Schuster, and D. D. Miller, Mol. Phys. 11, 597 (1966).
5. Bauman, H. F., J. E. Chilton, and R. Mauri, Lockheed Missiles and Space Co., Report No. AFAP-TR-66-35 (April 1966).
6. Wall, F. T., G. S. Stent, and J. J. Ondrejcin, J. Phys. & Colloid. Chem. 54, 979 (1950); see also Weissberger, A., Physical Methods of Organic Chemistry, Part IV, 3rd Ed. (1960), p. 3066.
7. Prue, J. E. and P. J. Sherrington, Trans. Faraday Soc. 57, 1795 (1961).

REPORT DISTRIBUTION LIST FOR
CONTRACT NO. NAS3-8521

National Aeronautics & Space Administration Scientific & Technical Information Facility Post Office Box 33 College Park, Maryland 20740 Attention: NASA Representative	(3)
National Aeronautics & Space Administration Washington, D. C. 20546 Attention: E. M. Cohn (RNW)	(1)
National Aeronautics & Space Administration Washington, D. C. 20546 Attention: A. M. Greg Andrus (FC)	(1)
National Aeronautics & Space Administration Goddard Space Flight Center Greenbelt, Maryland 20771 Attention: Thomas Hennigan (Code 716.2)	(1)
National Aeronautics & Space Administration Goddard Space Flight Center Greenbelt, Maryland 20771 Attention: E. R. Stroup (Code 636.2)	(1)
National Aeronautics & Space Administration Goddard Space Flight Center Greenbelt, Maryland 20771 Attention: Joseph Sherfey (Code 735)	(1)
National Aeronautics & Space Administration Langley Research Center Langley Station Hampton, Virginia 23365 Attention: John L. Patterson (MS-234) Instrument Research Division	(1)



National Aeronautics & Space Administration (1)
Langley Research Center
Langley Station
Hampton, Virginia 23365
Attention: M. B. Seyffert (MS-112)
Instrument Research Division

National Aeronautics & Space Administration (1)
Langley Research Center
Langley Station
Hampton, Virginia 23365
Attention: S. T. Peterson/Harry Ricker

National Aeronautics & Space Administration (1)
Lewis Research Center
21000 Brookpark Road
Cleveland, Ohio 44135
Attention: Dr. B. Lubarsky (MS 500-201)

National Aeronautics & Space Administration (1)
Lewis Research Center
21000 Brookpark Road
Cleveland, Ohio 44135
Attention: N. D. Sanders (MS 302-1)

National Aeronautics & Space Administration (1)
Lewis Research Center
21000 Brookpark Road
Cleveland, Ohio 44135
Attention: H. J. Schwartz (MS 500-202)

National Aeronautics & Space Administration (1)
Lewis Research Center
21000 Brookpark Road
Cleveland, Ohio 44135
Attention: Dr. J. S. Fordyce (MS 302-1)

National Aeronautics & Space Administration (1)
Lewis Research Center
21000 Brookpark Road
Cleveland, Ohio 44135
Attention: J. E. Dilley (MS 500-309)

National Aeronautics & Space Administration (1)
Lewis Research Center
21000 Brookpark Road
Cleveland, Ohio 44135
Attention: M. J. Saari (MS 500-202)

National Aeronautics & Space Administration (1)
Lewis Research Center
21000 Brookpark Road
Cleveland, Ohio 44135
Attention: J. J. Weber (MS 3-19)

National Aeronautics & Space Administration (2)
Lewis Research Center
21000 Brookpark Road
Cleveland, Ohio 44135
Attention: Robert B. King (MS 500-202)

National Aeronautics & Space Administration (1)
Lewis Research Center
21000 Brookpark Road
Cleveland, Ohio 44135
Attention: Library (MS 60-3)

National Aeronautics & Space Administration (1)
Lewis Research Center
21000 Brookpark Road
Cleveland, Ohio 44135
Attention: Report Control (MS 5-5)

National Aeronautics & Space Administration (1)
George C. Marshal Space Flight Center
Huntsville, Alabama 35812
Attention: Philip Youngblood

National Aeronautics & Space Administration (1)
George C. Marshal Space Flight Center
Huntsville, Alabama 35812
Attention: Richard Boehme (Bldg. 4487-EB)

National Aeronautics & Space Administration (1)
Manned Spacecraft Center
Houston, Texas 77058
Attention: William R. Dusenbury
Propulsion & Energy Systems Branch
(Bldg. 16, Site 1)

National Aeronautics & Space Administration (1)
Manned Spacecraft Center
Houston, Texas 77058
Attention: Robert Cohen
Gemini Project Office



National Aeronautics & Space Administration (1)
Manned Spacecraft Center
Houston, Texas 77058
Attention: Richard Ferguson (EP-5)

National Aeronautics & Space Administration
Manned Spacecraft Center
Houston, Texas 77058
Attention: Forrest E. Eastman (EE-4)

National Aeronautics & Space Administration (1)
Ames Research Center
Moffett Field, California. 94035
Attention: James R. Swain/A. S. Hertzog
Pioneer Project

National Aeronautics & Space Administration (1)
Ames Research Center
Moffett Field, California 94035
Attention: Jon Rubenzer
Biosatellite Project

Jet Propulsion Laboratory (1)
4800 Oak Grove Drive
Pasadena, California 91103
Attention: Aiji Uchiyama

Department of the Army

U. S. Army Engineer R & D Labs. (1)
Fort Belvoir, Virginia 22060
Attention: Electrical Power Branch (SMOFB-EP)

Commanding Officer (1)
U. S. Army Electronics R & D Labs.
Fort Monmouth, New Jersey 07703
Attention: Power Sources Division (SELRA/PS)

Research Office (1)
Rand D. Directorate
Army Weapons Command
Rock Island, Illinois 61201
Attention: Mr. G. Riensmith, Chief



U. S. Army Research Office (1)
Box CM, Duke Station
Durham, North Carolina 27706
Attention: Dr. Wilhelm Jorgensen

U. S. Army Research Office (1)
Chief, Rand D
Department of the Army
3D442, The Pentagon
Washington, D. C. 20546

Harry Diamond Laboratories (1)
Room 300, Building 92
Connecticut Avenue & Van Ness Street, N. W.
Washington, D. C. 20008
Attention: Nathan Kaplan

Army Materiel Command (1)
Research Division
AMCRD-RSCM-T-7
Washington, D. C. 20315
Attention: John W. Crellin

Army Materiel Command (1)
Development Division
AMCRD-DE-MO-P
Washington, D. C. 20315
Attention: Marshall D. Aiken

U. S. Army TRECOM (1)
Fort Eustis, Virginia 23604
Attention: Dr. R. L. Echols (SMOFFE-PSG)

U. S. Army TRECOM (1)
Fort Eustis, Virginia 23604
Attention: Leonard M. Bartone (SMOFFE-ASE)

U. S. Army Mobility Command (1)
Research Division
Warren, Michigan 48090
Attention: O. Renius (AMSMO-RR)



Natick Laboratories (1)
Clothing and Organic Materials Division
Natick, Massachusetts 01760
Attention: Norman Fertman

Department of the Navy

Office of Naval Research (1)
Washington, D. C. 20360
Attention: Head, Power Branch (Code 429)

Office of Naval Research (1)
Department of the Navy
Washington, D. C. 20360
Attention: H. W. Pox (Code 425)

Naval Research Laboratory (1)
Washington, D. C. 20390
Attention: Dr. J. C. White (Code 6160)

U. S. Navy Marine Engineering Laboratory (1)
Annapolis, Maryland 21402
Attention: J. H. Harrison

Bureau of Naval Weapons (1)
Department of the Navy
Washington, D. C. 20360
Attention: Whitewall T. Beatson (Code RAAE-52)

Bureau of Naval Weapons (1)
Department of the Navy
Washington, D. C. 20360
Attention: Milton Knight (Code RRRE-62)

Naval Ammunition Depot (1)
Crane, Indiana 47522
Attention: E. Bruess/H. Shultz

Naval Ordnance Laboratory (1)
Department of the Navy
Corona, California 91720
Attention: William C. Spindler (Code 441)

Naval Ordnance Laboratory (1)
Department of the Navy
Silver Spring, Maryland 20900
Attention: Philip B. Cole (Code WB)



Bureau of Ships (1)
Department of the Navy
Washington, D. C. 20360
Attention: C. F. Viglotti (Code 660)

Bureau of Ships (1)
Department of the Navy
Washington, D. C. 20360
Attention: Bernard B. Rosenbaum (Code 340)

Department of the Air Force

Space Systems Division (1)
Los Angeles Air Force Station
Los Angeles, California 90045
Attention: SSSD

Flight Vehicle Power Branch (1)
Aero Propulsion Laboratory
Wright-Patterson Air Force Base, Ohio 45433
Attention: James E. Cooper

Air Force Cambridge Research Lab. (1)
L. G. Hanscom Field
Bedford, Massachusetts 01731
Attention: Commander (CR0)

Headquarters, U. S. Air Force (AFRDR-AS) (1)
Washington 25, D. C.
Attention: Major G. Starkey

Headquarters, U. S. Air Force (AFRDR-AS) (1)
Washington 25, D. C.
Attention: Lt. Col. William G. Alexander

Rome Air Development Center, ESD (1)
Griffis Air Force Base, New York 13442
Attention: Frank J. Mollura (RASSM)

Other Government Agencies

National Bureau of Standards (1)
Washington, D. C. 20234
Attention: Dr. W. J. Hamer



Office, DDR&E, **USE & BSS**
The Pentagon
Washington, D. C. 20310
Attention: G. B. Wareham

(1)

Mr. Donald B. Hoatson
Army Reactors, DRD
U. S. Atomic Energy Commission
Washington, D. C. 20545

(1)

Institute for Defense Analyses
R & E Support Division
400 Army-Navy Drive
Arlington, Virginia 22202
Attention: Mr. R. Hamilton

(1)

Institute for Defense Analyses
R & E Support Division
400 Army-Navy Drive
Arlington, Virginia 22202
Attention: Dr. George C. Szego

(1)

U. S. Atomic Energy Commission
Auxiliary Power Branch (SNAP)
Division of Reactor Development
Washington 25, D. C.
Attention: Lt. Col. George H. Ogburn, Jr.

(1)

Lt. Col. John H. Anderson
Advanced Space Reactor Branch
Division of Reactor Development
U. S. Atomic Energy Commission
Washington 25, D. C.

(1)

Clearing House
5285 Park Royal Road
Springfield, Virginia 22151

(1)

Industry

Aerojet-General Corporation
Von Karman Center
Bldg. 312, Dept. 3111
Azusa, California
Attention: Mr. Russ Fogle

(1)

Aeronutronic Division Philco Corporation Ford Road Newport Beach, California 92660	(1)
Aerospace Corporation Post Office Box 95085 Los Angeles, California 90045 Attention: Library	(1)
Aerospace Corporation Systems Design Division 2350 East El Segundo Boulevard El Segundo, California Attention: John G. Krisilas	(1)
Allis-Chalmers Manufacturing Co. 1100 South 70th Street Milwaukee, Wisconsin 53201 Attention: Dr. P. Joyner	(1)
American University Mass. & Nebraska Avenues, N. W. Washington, D. C. 20016 Attention: Dr. R. T. Foley, Chemistry Department	(1)
Arthur D. Little, Inc. Acorn Park Cambridge, Massachusetts 02140 Attention: Dr. Ellery W. Stone	(1)
Atomics International Division North American Aviation, Inc. 8900 De Soto Avenue Canoga Park, California 91304 Attention: Dr. H. L. Recht	(1)
Battelle Memorial Institute 505 King Avenue Columbus, Ohio 43201 Attention: Dr. C. L. Faust	(1)

Bell Telephone Laboratories, Inc. Murray Hill, New Jersey 07971 Attention: U. B. Thomas	(1)
The Boeing Company P. O. Box 3707 Seattle, Washington 98124	(1)
Borden Chemical Company Central Research Laboratory P. O. Box 9524 Philadelphia, Pennsylvania 19124	(1)
Burgess Battery Company Foot of Exchange Street Freeport, Illinois 61032 Attention: Dr. Howard J. Strauss	(1)
C & D Batteries Division of Electric Autolite Col. Conshohocken, Pennsylvania 19428 Attention: Dr. Eugene Willihnganz	(1)
Calvin College Grand Rapids, Michigan 49506 Attention: Prof. T. P. Dirkse	(1)
Catalyst Research Corporation 6101 Falls Road Baltimore, Maryland 21209 Attention: J. P. Wooley	(1)
Chem-Cell Inc. 150 Dey Road Wayne, New Jersey 07470 Attention: Peter D. Richman	(1)
Delco Remy Division General Motors Corporation 2401 Columbus Avenue Anderson, Indiana 46011 Attention: Dr. J. J. Lander	(1)
Douglas Aircraft Company, Inc. Astropower Laboratory 2121 Campus Drive Newport Beach, California 92663 Attention: Dr. Carl Berger	(1)



Dynatech Corporation (1)
17 Tudor Street
Cambridge, Massachusetts 02138
Attention: R. L. Wentworth

Eagle-Picher Company (1)
Post Office **Box** 47
Joplin, Missouri 64802
Attention: E. M. Morse

Elgin National Watch Company (1)
107 National Street
Elgin, Illinois 60120
Attention: T. Boswell

Electric Storage Battery Company (1)
Missile Battery Division
2510 Louisburg Road
Raleigh, North Carolina 27604
Attention: A. Chreitzberg

Electric Storage Battery Company (1)
Carl F. Norberg Research Center
19 West College Avenue
Yardley, Pennsylvania 19068
Attention: Dr. R. A. Scliaefer

Electrochimica Corporation (1)
1140 O'Brien Drive
Menlo Park, California 94025
Attention: Dr. Morris Eisenberg

Electro-Optical Systems, Inc. (1)
300 North Halstead
Pasadena, California 91107
Attention: M. Klein

Emhart Manufacturing Company (1)
Box 1620
Hartford, Connecticut 06101
Attention: Dr. W. P. Cadogan

Engelhard Industries, Inc. (1)
497 DeLancy Street
Newark, New Jersey 07105
Attention: Dr. J. G. Cohn

Dr. Arthur Fleischer (1)
466 South Center Street
Orange, New Jersey 07050

General Electric Company (1)
Research & Development Center
Schenectady, New York 12301
Attention: Dr. R. C. Osthoff
(Bldg. 37, Room 2083)

General Electric Company (1)
Missile & Space Division
Spacecraft Department
P. O. Box 8555
Philadelphia, Pennsylvania 19101
Attention: E. W. Kipp, Room T-2513

General Electric Company (1)
Battery Products Section
P. O. Box 114
Gainesville, Florida 32601

General Electric Company (1)
Research & Development Center
Schenectady, New York 12301
Attention: Dr. H. Liebhafsky

General Motors Corporation (1)
Defense Research Laboratories
6767 Hollister Street
Santa Barbara, California 93105
Attn: Dr. J. S. Smatko/Dr. C. R. Russell

General Telephone & Electronics Labs. (1)
Bayside, New York
Attention: Dr. Paul Goldberg

Globe-Union Inc. (1)
900 East Keefe Avenue
Milwaukee, Wisconsin 53201
Attention: Dr. Warren Towle

Globe-Union Inc. (1)
900 East Keefe Avenue
Milwaukee, Wisconsin 53201
Attention: Dr. C. K. Morehouse



Gould-National Batteries, Inc. (1)
Engineering & Research Center
2630 University Avenue, S. E.
Minneapolis, Minnesota 55418
Attention: D. L. Douglas

Gulton Industries (1)
Alkaline Battery Division
212 Durham Avenue
Metuchen, New Jersey 08840
Attention: Dr. Robert Shair

Grumman Aircraft (1)
OPGS, Plant 35
Bethpage, Long Island, N. Y.
Attention: Bruce Clark

Hughes Aircraft Corporation (1)
Centinda Avenue & Teale Street
Culver City, California 90230
Attention: T. V. Carvey

Hughes Aircraft Corporation (1)
Bldg. 366, M. S. 524
El Segundo, California 90245
Attention: R. B. Robinson

Hughes Research Labs. Corp. (1)
3011 Malibu Canyon Road
Malibu, California 90265
Attention: T. M. Hahn

ITT Federal Laboratories (1)
500 Washington Avenue
Nutley, New Jersey 07110
Attention: Dr. P. E. Lighty

ITT Research Institute (1)
10 West 35th Street
Chicago, Illinois 60616
Attention: Dr. H. T. Francis



Institute of **Gas** Technology (1)
State and 34th Street
Chicago, Illinois 60616
Attention: B. S. Baker

Johns Hopkins University (1)
Applied Physics Laboratory
8621 Georgia Avenue
Silver Spring, Maryland 20910
Attention: Richard Cole

Johns-Manville R & E Center (1)
P. O. **Box** 159
Manville, New Jersey 08835
Attention: J. S. Parkinson

Leesona Moos Laboratories (1)
Lake Success Park, Community Drive
Great Neck, New **York** 11021
Attention: Dr. H. Oswin

Livingston Electronic Corporation (1)
Route 309
Montgomeryville, Pennsylvania 18936
Attention: William F. Meyers

Lockheed Missiles & Space Company (1)
3251 Hanover Street
Palo Alto, California 94304
Attention: Library/Dr. **G. B.** Adams

Lockheed Missiles & Space Company (1)
Dept. 62-30
3251 Hanover Street
Palo Alto, California 94304
Attention: J. **E.** Chilton

Idaho State University (1)
Department of Chemistry
Pocatello, Idaho 83201
Attention: Dr. G. Myron Arcand



Mallory Battery Company
60 Elm Street
North Tarryton, New York 10593
Attention: R. R. Clune

(1)

P. R. Mallory & Company, Inc.
Technical Services Laboratory
Indianapolis, Indiana 46206
Attention: A. S. Doty

P. R. Mallory & Company, Inc.
Northwest Industrial Park
Burlington, Massachusetts 02103
Attention: Dr. Per Bro

(1)

P. R. Mallory & Company, Inc.
3029 East Washington Street
Indianapolis, Indiana 46206
Attention: Technical Librarian

(1)

Marquardt Corporation
16555 Saticoy Street
Van Nuys, California 91406
Attention: Dr. H. G. Krull

(1)

Material Research Corporation
Orangeburg, New York
Attention: V. E. Adler

(1)

Melpar
Technical Information Center
3000 Arlington Boulevard
Falls Church, Virginia 22046

(1)

Midwest Research Institute
425 Volker Boulevard
Kansas City, Missouri 64110
Attention: Dr. B. W. Beadle

(1)

Monsanto Research Corporation
Boston Laboratory
Everett, Massachusetts 02149
Attention: Dr. J. O. Smith

(1)

North American Aviation, Inc.
Rocketdyne Division
6633 Canoga Avenue
Canoga Park, California 91303
Attention: Library

(1)



North American Aviation, Inc. (1)
12214 Lakewood Boulevard
Downey, California 90241
Attention: Burton M. Otzinger

Dr. John Owen (1)
P. O. Box 87
Bloomfield, New Jersey 07003

Power Information Center (1)
University of Pennsylvania
Moore School Building
200 South 33rd Street
Philadelphia, Pennsylvania 19104

Philco Corporation (1)
Division of the Ford Motor Company
Blue Bell, Pennsylvania 19422
Attention: Dr. Phillip Cholet

Radiation Applications, Inc. (1)
36-40 37th Street
Long Island City, New York 11101

Radio Corporation of America (1)
Astro Division
Hightstown, New Jersey 08520
Attention: Seymour Winkler

Radio Corporation of America (1)
P. O. Box 800
Princeton, New Jersey 08540
Attention: I. Schulman

Southwest Research Institute (1)
8500 Culebra Road
San Antonio, Texas 78206
Attention: Dr. Jan Al

Sonotone Corporation (1)
Saw Mill River Road
Elmsford, New York 10523
Attention: A. Mundel

Texas Instruments, Inc. (1)
Metals and Controls Division
34 Forest Street
Attleboro, Massachusetts 02703
Attention: Dr. E. M. Jost



Texas Instruments, Inc. (1)
13500 North Central Expressway
Dallas, Texas 75222
Attention: Dr. Isaac Trachtenberg

Thomas A. Edison Research Laboratory (1)
McGraw Edison Company
Watchung Avenue
West Orange, New Jersey 07052
Attention: Dr. P. F. Grieger

TRW Systems, Inc. (1)
One Space Park
Redondo Beach, California 90278
Attention: Dr. A. Krausz
(Bldg. 60, Rm. 929)

TRW Systems, Inc. (1)
One Space Park
Redondo Beach, California 90278
Attention: Mr. Richard Sparks

TRW Inc. (1)
23555 Euclid Avenue
Cleveland, Ohio 44117
Attention: Librarian

Tyco Laboratories, Inc. (1)
Bear Hill
Hickory Drive
Waltham, Massachusetts 02154
Attention: W. W. Burnett

Union Carbide Corporation (1)
Development Laboratory Library
P. O. Box 6056
Cleveland, Ohio 44101

Union Carbide Corporation (1)
Parma Research Laboratory
P. O. Box 6116
Cleveland, Ohio 44101
Attention: Library

University of California (1)
Space Science Laboratory
Berkeley, California 94720
Attention: Dr. C. W. Tobias



University of Pennsylvania
Electrochemistry Laboratory
Philadelphia, Pennsylvania 19104
Attention: Prof. J. O'M. Bockris

(1)

Western Electric Company
Suite 802, RCA Building
Washington, D. C. 20006
Attention: R. T. Fiske

(1)

Westinghouse Electric Corporation
Research & Development Center
Churchill Borough
Pittsburgh, Pennsylvania 15235
Attention: Dr. A. Langer

(1)

Whittaker Corporation
3850 Olive Street
Denver, Colorado 80237
Attention: Borch Wendir

(1)

Whittaker Corporation
NARMCO Research & Development Division
3540 Aero Court
San Diego, California 92123
Attention: Dr. M. Shaw

(1)

Yardney Electric Corporation
Yardney Building
40-52 Leonard Street
New York, New York 10013
Attention: Dr. George Dalin

(1)

1. ORIGINATING ACTIVITY (Corporate author)		2. REPORT SECURITY CLASSIFICATION	
Rocketdyne, a Division of North American Aviation, Inc., 6633 Canoga Avenue, Canoga Park, California		UNCLASSIFIED	
3. REPORT TITLE		2b. GROUP	
PROPERTIES OF NONAQUEOUS ELECTROLYTES			
4. DESCRIPTIVE NOTES (Type of report and inclusive dates)			
Quarterly Report (20 December 1966 to 19 March 1967)			
5. AUTHOR(S) (Last name, first name, initial)			
Keller, R.; Foster, J. N.; Hon J. F.; Sullivan, J. M.			
6. REPORT DATE	7a. TOTAL NO. OF PAGES	7b. NO. OF REFS	
19 April 1967	90	7	
8a. CONTRACT OR GRANT NO.	9a. ORIGINATOR'S REPORT NUMBER(S)		
NAS3-8521	R-6754-3		
b. PROJECT NO.	9b. OTHER REPORT NO(S) (Any other numbers hat may be assigned this report)		
c.			
d.			
10. AVAILABILITY/LIMITATION NOTICES			
11. SUPPLEMENTARY NOTES		12. SPONSORING MILITARY ACTIVITY	
		National Aeronautics and Space Administration, Lewis Research Center,	
<p>1</p> <p>content of each solvent is determined quantitatively to ± 5 to 10 ppm. Structural studies of electrolytes containing tetramethylammonium hexafluorophosphate ($\text{TMA} \cdot \text{PF}_6$), $\text{TMA} \cdot \text{F}$ and AlCl_3 were performed by nuclear magnetic resonance. The physical property studies included measurements of viscosities, conductances, transference numbers, and solubilities of a number of electrolytes.</p>			

UNCLASSIFIED

Security Classification

14. KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Nonaqueous Electrolytes						
Acetonitrile						
Propylene Carbonate						
N,N-Dimethyl Formamide						
Tetramethylammonium Hexafluorophosphate						

INSTRUCTIONS

1. **ORIGINATING ACTIVITY** Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (corporate author) issuing the report.

21. **REPORT SECURITY CLASSIFICATION:** Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. **GROUP:** Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. **REPORT TITLE** Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parentheses immediately following the title.

4. **DESCRIPTIVE NOTES:** If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

5. **AUTHOR(S):** Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. **REPORT DATE:** Enter the date of the report as day, month, year; or month, year. If more than one date appears on the report, use date of publication.

7a. **TOTAL NUMBER OF PAGES:** The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. **NUMBER OF REFERENCES:** Enter the total number of references cited in the report.

8a. **CONTRACT OR GRANT NUMBER:** If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, 8c, & 8d. **PROJECT NUMBER:** Enter the appropriate military department identification, which is project number, subproject number, system numbers, task number, etc.

9a. **ORIGINATOR'S REPORT NUMBER(S):** Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. **OTHER REPORT NUMBER(S):** If the report has been assigned any other report numbers (either by the originator or by the sponsor), also enter this number(s).

10. **AVAILABILITY/LIMITATION NOTICE:** Enter any limitations on further dissemination of the report, other than those

imposed by security classification, using standard statements such as:

- (1) "Qualified requesters may obtain copies of this report from DDC."
- (2) "Foreign announcement and dissemination of this report by DDC is not authorized."
- (3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through _____."
- (4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through _____."
- (5) "All distribution of this report is controlled. Qualified DDC users shall request through _____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. **SUPPLEMENTARY NOTES:** Use for additional explanatory notes.

12. **SPONSORING MILITARY ACTIVITY:** Enter the name of the departmental project office or laboratory sponsoring (pay for) the research and development. Include address.

13. **ABSTRACT:** Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. **KEY WORDS:** Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, rules, and weights is optional.

UNCLASSIFIED

Security Classification